

**MS Word Export To Multiple PDF Files Software - Please purchase
license. SECTION 1
1.2 Results Summary
Theater**

ACM SURVEY RESULTS

The following homogeneous building material types were sampled as part of this survey conducted May 27, 2003. Results are summarized in the table below:

MTL #	MATERIAL DESCRIPTION	LOCATION	F/NF ¹	COND. ²	% ACM	# SAMP.	QUANTITY
01	Drywall (orange) Joint compound*	181	F	Good	ND	3	N/A
02	Spray-on ceiling material	Entrance area next to 182	F	Good	<1%	3	300 SF
03	Black cove base/ mastic	All rooms except southeast exit, 160, northwest exit, 170, 178, mech. rooms, 109a, 193, 191, 195	NF	Good	Cove base = ND Mastic = 2%	3	2,500 SF
04	Vibration joint cloth	170, 183, 182, 184, 184a, 184c, 188d, 190a, 194, 195, WRR, MRR, 193, 191	NF	Good	ND	3	N/A
05	Drywall (white) Joint compound*	All rooms except southeast exit, 160, northwest exit, 170, 182	F	Good	Drywall = ND JC = < 1%	3	65,000 SF
06	Black flooring material/mastic	182, 170, 178	NF	Good	Flooring = ND Backing = ND	3	N/A
07	Red carpet mastic	Southeast exit, 160, 162, Northwest exit, 170, 178	NF	Good	ND	3	N/A
08	2' x 4' White ceiling panel	MRR, WRR, 188, 188b, 190, 190a, WRR(195), MRR(193)	F	Good	ND	3	N/A
09	TSI pipe insulation	Mech. room, 188b, 190a, 195, WRR(195), 193, MRR(193)	F	Good	10%	3	300 LF
10	Drywall (yellow) Joint compound*	184a, 184b	F	Good	Drywall = ND JC = <1%	3	2,000 SF
11	Black sink undercoating	184b, 187	NF	Good	ND	3	N/A
12	Yellow rolled sheet flooring	Elevator	F	Good	10%	3	150 SF
13	Yellow cove base/ mastic	Elevator	NF	Good	Cove base = ND Mastic = ND	3	N/A
14	12" x 12" White floor tile/mastic	Rear entrance, 195, 193, 191, 187	NF	Good	Floor tile = 2% Mastic = 5%	3	3,000 SF
15	Tan cove base/ mastic	195, 193, 191, 187	NF	Good	Cove base = ND Mastic = 2%	3	200 SF
16	White hard plaster	195	F	Good	ND	3	N/A
17	1' x 1' White ceiling tile	184a, 191, 193, 194, 195, 187	F	Good	ND	3	N/A
18	Brown cove base/ mastic	194	NF	Good	Cove base = ND Mastic = ND	3	N/A
19	Vibration joint cloth	78, 78b	NF	Good	ND	3	N/A
20	Drywall (white) Joint compound*	78, 78a, 78b, 78c	F	Good	Drywall = ND JC = ND	3	N/A
21	Black cove base/ mastic	78, 78b, 78c	NF	Good	Cove base = ND Mastic = 2%	3	150 SF

